

EXILVA FOR CONSTRUCTION

## EXILVA CELLULOSE FIBRILS IN **SELF-COMPACTING CONCRETE (SCC)**

Concrete products are complex mixtures of cement, water, chemicals, fines, and heavy particles. The biggest challenges are typically related to the control of stability, flow, placement, finishing and strength.

Bleeding and particle segregation are two significant challenges with fluid concrete (S3-S4/F4-F6). These issues are normally managed by adding fine particles, a filler, stabilizers or combinations of these. Viscosity modifying agents (VMA) like cellulose ethers, natural gums (xanthan, gellan) and starch are often used in concrete as stabilizers. They mainly act by increasing the paste viscosity thereby reducing the risks of bleeding and segregation.

### WHY CAN EXILVA HELP YOU?

#### – YIELD STRESS, WATER RETENTION AND SHEAR THINNING.

By forming a non-soluble three-dimensional network, Exilva stabilizes the various particles, present in concrete, physically inside this network, preventing settling and enhancing the stability of the concrete at rest. The high hydrophilicity of Exilva ensures that water is bound strongly to the fibers, providing sufficient water retention to the concrete, without having any negative effect on the setting time. Exilva possesses extreme shear thinning properties, allowing you to pump and spray efficiently even with thick concrete mixtures. Exilva is highly tolerant and stable under a wide range of different conditions (temperature, pH 1-13 and shear), enabling you to create stable concrete mixtures for use in a high variety of geographical markets. Exilva provides constant performance regardless of the surrounding temperature (10-90 °C), even during hot summer months.



European project funded by the Bio Based Industries Joint Undertaking under the European Union's Horizon 2020 research and innovation program under grant agreement N° 709746.

A product by  Borregaard

## SELF-COMPACTING CONCRETE MIXTURES

The effect of Exilva to the bleeding, segregation and flow of SCC mixtures were studied. Exilva P 01-L was added as is and the amount of water in the mixtures was adjusted accordingly, taking into account the water present in Exilva P 01-L.

TABLE 1: Concrete mixes. <sup>1</sup>Water to cement ratio, <sup>2</sup>Solid by weight of cement.

	Reference	With Exilva P 01-L 0.75 % sbwc <sup>2</sup>	With Exilva P 01-L 1.50 % sbwc <sup>2</sup>
Gravel	Amount [kg]	Amount [kg/m <sup>3</sup> ]	Amount [kg/m <sup>3</sup> ]
20/10	105	105	105
10/4	703	703	703
4/0	289	289	289
2/0	604	604	604
Std cement CEM II	376	376	376
Water	235	220	204
Exilva P 01-L	–	2.82	5.60
w/c <sup>1</sup>	0.63	0.63	0.63
PCE sbwc %	0.40	0.40	0.40

## EVALUATION

The performance of SCC mixtures were measured using the flow test. The setting time and strength were analyzed according to EN 123 and EN 456.

TABLE 2: Evaluation of SCC mixtures.

Slump flow [mm]	Reference	With Exilva P 01-L 0.75 % sbwc	With Exilva P 01-L 1.50 % sbwc
Initial	695	665	655
60 min	665	655	645
120 min	660	670	635
180 min	655	635	615
<b>Time of spread [s]</b>			
Initial	15	13	15
60 min	16	17	18
120 min	16	18	18
180 min	16	18	15
Setting time [h]	9.9	9.7	9.8
<b>Strength [MPa]</b>			
2 days	10.4	10.8	9.6
7 days	18.3	18.2	18.3
28 days	34.4	35.5	32.3

The following figures (1-3) demonstrate how Exilva P 01-L stabilizes concrete mixtures, compared to the reference mixture. An addition of 0.75% sbwc of Exilva P 01-L prevents segregation and bleeding without impacting the “time to flow”, which can, to some extent, be related to viscosity. Increasing the amount of Exilva P 01-L results in decrease in flow, but without having any effect to the setting time. In addition, Exilva P 01-L has no detrimental effect on workability retention on low dosage levels, contrary to silica fumes for instance, which are also frequently used to stabilize highly fluid mixes.



FIGURE 1: Reference concrete mix at initial spread



FIGURE 2: Concrete mix with 0.75 % sbwc of Exilva at initial spread



FIGURE 4: Concrete mix with 1.50 % sbwc of Exilva at initial spread

## SUMMARY

Exilva prevents effectively segregation, settling and bleeding of concrete. Exilva provides water retention without impacting set times nor strength development of concrete. Exilva also increases the workability of concrete, providing sag resistant, non-sticky and easily spreadable concrete mixtures. Exilva is delivered as a pre-activated product, meaning that no additional hydration steps are needed.

## UNIQUE ADVANTAGES

- Rheology control – enhances yield stress, giving strong thickening and shear thinning
- Creates non-sticky and non-plastic concrete
- Versatile and robust – stable in extreme environments, including pH, temperature and shear
- Increases stability of end products
- 100% natural and infinitely sustainable – can reduce the CO2 footprint in concrete
- Very efficient at low dosage
- Odor free, clean and white

## OTHER POTENTIAL APPLICATIONS

- Underwater concrete
- Sprayed concrete
- Sprayed micro-concrete and mortar
- Oil well cementing
- Bore piled concrete
- Grouting
- Mass concrete
- Non-sticky overhead (repair) concrete
- Cement skim coat
- Self-leveling underlayment
- Compacting aid for vibrated precast concrete

### Disclaimer

The information contained in this technical guide on Exilva MFC products and their possible application is for general information purposes only. The information is provided by Borregaard AS and while we endeavour to keep the information up to date and correct, we make no representations or warranties of any kind, express or implied, about the completeness, accuracy, reliability, suitability or availability with respect to the information contained in the Technical Guide for any purpose. Any reliance you place on such information is therefore strictly at your own risk. In no event will we be liable for any loss or damage including without limitation, direct, indirect or consequential loss or damage, or any loss or damage whatsoever arising from loss of data or profits arising out of, or in connection with, the use of the information. Construction of the disclaimers above and resolution of disputes thereof are governed by Norwegian law.